Sani * Tech[®] STHT[®]-WR Wire-Reinforced Silicone Hose



Sani-Tech® STHT®-WR is an ultra-flexible, high-pressure, platinum-cured silicone hose.

Sani-Tech® STHT®-WR Wire-Reinforced Silicone Hose

Sani-Tech STHT-WR platinum-cured silicone, wire-reinforced hose, constructed of multi-ply reinforcement and 316L SS helical wire, provides unsurpassed flexibility while maintaining high-pressure ratings with full vacuum capabilities. Sani-Tech STHT-WR is manufactured with an ultra-pure, biopharmaceutical-grade silicone to ensure your process integrity.

Characteristics

The manufacturing process is carefully controlled from receiving through production. Inspection and lot traceability is readily accessible as batch numbers are assigned. All packages are identified by external labeling on both the bag and the high-quality, crush-proof box.

Saint-Gobain Performance Plastics' manufacturing facility has the ability to create a variety of unique color-coding systems for your particular application needs. STHT-WR is available in custom-coded coloring.

Biocompatibility

Sani-Tech STHT-WR is manufactured from the finest grade of silicone materials and is fully characterized, validated and tested to a variety of specifications including USP Class VI criteria, ISO 10993 and European Pharmacopoeia 3.1.9. Sani-Tech STHT-WR platinum-cured braid-reinforced silicone hose has a masterfile with the U.S. Food and Drug Administration. For additional compliance data, please review characterization information on the back page.

BIOPHARMACEUTICAL PRODUCTS

Platinum-Cured Wire-Reinforced Silicone Hose

Features/Benefits

- Biopharmaceutical grade
- Ultra-flexible bend radius
- Available in 25-foot standard lengths
- Unsurpassed inner surface smoothness
- Autoclavable and sterilizable
- Temperature range from -80°F (-62°C) to 500°F (260°C)
- Imparts no taste or odor
- Custom color-coding available
- Meets all USP Class VI, EP 3.1.9 FDA and ISO criteria
- High-pressure and vacuum rating
- Lot number traceability

Typical Applications

- Biopharmaceutical manufacturing
- Pharmaceutical processing and production
- Vacuum pump applications
- Bulk transfer
- Load cell
- Bioreactor process lines
- Production fermentation

Connections

- Sanitary, non-metallic fittings
- Radially crimped 316L SS or non-metallic fittings
- Adapter connections

SAINT-GOBAIN

Sani-Tech[®] STHT[®]-WR Hose Inventory Sizes

| Part Number | ID Inches (mm) | OD Inches (mm) | Wall Inches | Maximum Working Pressure PSI at 68°F | Minimum Burst Pressure PSI at 68°F | Minimum Bend Radius Inches | Weight Per Foot Lb. | Vacuum Rating IN. HG |
|----------------|-------------------|-------------------|----------------|---|---|----------------------------------|---------------------------|----------------------------|
| STHT-WR-0500 | .500 (12.70) | .920 (23.37) | .210 | 150 | 600 | 1.5 | .25 | 29.9 |
| STHT-WR-0750 | .750 (19.05) | 1.190 (30.23) | .220 | 125 | 500 | 2.5 | .36 | 29.9 |
| STHT-WR-1000 | 1.000 (25.40) | 1.450 (36.83) | .225 | 125 | 500 | 4.0 | .48 | 29.9 |
| STHT-WR-1500 | 1.500 (38.10) | 2.160 (54.86) | .330 | 125 | 500 | 5.5 | 1.00 | 29.9 |
| STHT-WR-2000 | 2.000 (50.80) | 2.690 (68.33) | .345 | 100 | 400 | 7.0 | 1.25 | 29.9 |

Characterization

The biocompatibility of STHT platinum-cured silicone hose, manufactured with Sani-Tech silicone, has been tested and complies with the parameters set forth in the following test protocols:

- USP XXIV (88) biological reactivity, in vivo
- Intracutaneous test, Systemic injection test, Implantation test
 USP XXIV (87) biological reactivity, in vitro
- L929 MEM elution, AGAR diffusion
- ISO 10993
- FDA CFR 177.2600
- Meets or exceeds USDA standard and 3A approval
- European Pharmacopoeia 3.1.9

Sterilization Methods

- Autoclavable
- Radiation up to 5.0 Mrad (50 Kilogray)
- Gas Ethylene Oxide

NOTE: STHT hose will not deteriorate with repeated autoclaving. This method of sterilization is strongly recommended. STHT silicones should not be considered for consistent steam applications.

WARNING: Do not use STHT silicone hose in hot oil or acid applications.

Typical Physical Properties

| Property | ASTM Method | Value or Rating |
|--|-------------|-----------------|
| Durometer Hardness Shore A, 15 Sec | D2240 | 65 |
| Tensile Strength psi (MPa) | D412 | 1291 |
| Ultimate Elongation, 100% | 6 D412 | 693 |
| Tear Resistance Ib-f/inch (kN/m) | D624 | 329 |
| Specific Gravity | D792 | 1.19 |
| Tensile Modulus @ 100% Elongation, psi (MPa) | D412 | 351 |

Unless otherwise noted, all tests were conducted at room temperature (73°F). Values shown were determined on 0.075" thick extruded strip or 0.075" thick molded ASTM plaques or molded ASTM durometer buttons.

Sani-Tech® and STHT® are registered trademarks of Saint-Gobain Performance Plastics.

SANI-TECH[®] HOSE IS NOT INTENDED FOR USE AS AN IMPLANT MATERIAL

Leading the way in Critical Fluid Transfer and Containment

Saint-Gobain Performance Plastics 3910 Terry-Diane Street Beaverton, MI 48612 Tel: (888) 387-0067 Tel: (989) 435-9533 Fax: (989) 435-2355



IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics tubing for all intended uses. Laboratory and clinical tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of tubing in any particular application.

For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use, this product. THIS WARRANTY IS IN LIEU OF THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED. No deviation is authorized.

Saint-Gobain Performance Plastics Corporation assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to those products. All such advice is given and accepted at the buyer's risk.